BRUXSAFOL

TRUE VUE 5

DUAL REFLECTIVE – EXTRA DARK | INSIDE INSTALLATION

Sun protection film for the maximum heat reduction combined with strong darkening effect (blending reduction). Standout feature of this film: strong mirror effect on the outside (depending on light conditions), but with minimal reflexion on the room side. Neutral grey coloring. Energy saving by reducing cooling costs.

Performance Results (EN 410)	4 mm Single	4/12/4 mm Double
Visible Light		
Transmittance (VLT) %	5	5
Reflectance exterior / interior %	45/8	46/8
Glare reduction %	94	94
Solar Energy		
Transmittance %	6	5
Absorptance %	47	52
Reflectance %	47	43
UV protection [300 - 380 nm] %	>99	>99
Solar heat gain coefficient (g-value)	0,16	0,31
Light to solar heat gain ratio (VLT/SHGC)	0,32	0,16
Total solar energy rejected [90°] %	84	69
Total solar energy rejected [60°] %	85	73
UV Tdw-ISO [300 - 700 nm] %	5	4
Fade reduction %	94	95
Film thickness	50 µm	



SUN PROTECTION FILM

Film Performance (on 4 mm float glass)



Material Construction Self Adhesive Film

- Multi-layer metalized fim.
- Scratch resistant hard coat on the surface.
- Siliconised liner on the adhesive.
- High quality pressure sensitive adhesive system (water activated) with integrated UV-absorber for best longevity.

Flammability	IAW EN 13501-1: B/s1/d0
BRUXSAFOL Warranty	10 years
Storage	Recommended at +15° C up to +25° C and rel. humidity 50%: approx. 3 years
Possible Widths	☑ 183 cm ☑ 152 cm ☐ 122 cm ☐ 91 cm

Film-to-Glass-Guide

Single pane clear or tinted	●
Double pane clear or tinted	●
Double pane Low-e on #2	●
Double pane Low-e on #3	▲
Triple pane Low-e	■

● Low risk
▲ Caution! Submit Film-to-Glass application for risk assessment.
■ Tempered only

For further details please view:
www.bruxsafol.de/download/ftg-guide.pdf

All rights and errors reserved.
Technical data calculated using „Window 7.2." according to EN 410 and EN 673.

03/2025

BRUXSAFOL Folien GmbH · Thüringenstraße 2 · 97762 Hammelburg · **Tel. +49 97 32 / 78 73 - 0** · info@bruxsafol.com · **www.bruxsafol.com**